



Contribution ID: 304

Type: Poster

Composite Dust-Suppressing Coatings Containing Nanosized Sorbents Selective to Cesium, Cobalt, and Nickel Radionuclides

Tuesday, 13 May 2014 17:15 (1h 30m)

Here we report on development, characterization and performance evaluation of new materials based on selective to radionuclides nanosized sorbents stabilized in water dispersible nanoparticles (latexes). These new materials can be applicable as fixatives (dust suppressors), when latexes are film-forming, and as colloid stable sorbents for decontamination of solid bulk materials, when any type of latex, preferably containing carboxylic groups on the surface, is used.

Two different series of polymeric nanoparticles were synthesized and tested as a polymer matrix for inorganic sorbents immobilization. The first type of particles was based on polystyrene and composed of polystyrene either pure (homopolymer) or copolymerized with different amounts of acrylic acid in order to obtain carboxyl-functionalized latex particles. The second type was poly(silane acrylate)-based copolymer nanoparticles, consisting from butyl acrylate, methyl methacrylate, polymerizable silane and functional comonomer (either methacrylic acid or aminoethyl methacrylate hydrochloride). All particles were synthesized in direct (oil-in-water) miniemulsion system by free-radical (co)polymerization.

As selective inorganic materials colloidal SnO_2 and MnO_2 with mean particle size 10 nm and 200 nm, respectively, have been synthesized. Co(II) ferrocyanides were synthesized directly in the presence of carboxylic latex particles. Composites containing SnO_2 nanoparticles selective to radionuclides of nickel and cobalt have been prepared using carboxylic and aminolatexes as a matrix, the maximum loading degree was about 60 mg of SnO_2 per 1 g of latex. Sorption properties of composite latex/inorganic sorbent materials have been investigated toward ^{63}Ni , ^{57}Co (SnO_2), ^{137}Cs (Co(II) ferrocyanides), ^{90}Sr (manganese oxides) in the presence of competing ions. Distribution coefficients up to 105 ml/g were reached for cesium radionuclides and for nickel and cobalt radionuclides on SnO_2 in NaNO_3 solutions. The highest distribution coefficients of ^{90}Sr (~3500 ml/g) in the presence of competing Ca^{2+} ions (0.1 g/L) were reached for manganese oxides.

Dust suppressing formulations based on film-forming poly(silane acrylate) latexes containing Co(II) ferrocyanide and poly(silane aminoethyl) latexes containing SnO_2 have been prepared and drop casted on model contaminated sand. The leaching of ^{137}Cs and ^{57}Co radionuclides from coated sand surface was efficiently suppressed (leaching degree below 1%), when the content of Co(II) ferrocyanide and SnO_2 in composite coatings was as low as $1.3 \cdot 10^{-6}$ mol/cm³ and $8.3 \cdot 10^{-4}$ mol/cm³, respectively.

Acknowledgements: Financial support for ERANET-Russia project (STProject-144) of the 7th EU Research Framework Programme is gratefully acknowledged.

Primary authors: Dr KOIVULA, Risto (Laboratory of Radiochemistry, University of Helsinki, Finland); Dr BRATSKAYA, Svetlana (Institute of Chemistry FEBRAS, Vladivostok, Russia); Prof. AVRAMENKO, Valentin (Institute of Chemistry FEBRAS, Vladivostok, Russia); Dr ZHELEZNOV, Veniamin (Institute of Chemistry FEBRAS, Vladivostok, Russia)

Co-authors: Dr MIRONENKO, Alexander (Institute of Chemistry FEBRAS, Vladivostok, Russia); Dr SYNYT-SKA, Alla (Leibniz-Institut für Polymerforschung, Dresden, Germany); Dr MYSYANOVICH, Anna (Max-Planck-Institut für Polymerforschung, Mainz, Germany); Dr MARININ, Dmitry (Institute of Chemistry FEBRAS, Vladivostok, Russia); Dr SIMON, Frank (Leibniz-Institut für Polymerforschung, Dresden, Germany); Prof. HARJULA,

Risto (Laboratory of Radiochemistry, University of Helsinki, Finland)

Presenter: Dr MARININ, Dmitry (Institute of Chemistry FEBRAS, Vladivostok, Russia)

Session Classification: Poster Session - Radionuclides in the Environment, Radioecology

Track Classification: Radionuclides in the Environment, Radioecology